Docket number: 758/12810.114

AMENDMENTS TO THE CLAIMS: This listing of claims will replace prior versions and listings

of claims in the application:

Claim 1 has been cancelled, and claims 2, 5, 13, 37, 39, 41 and 43 have been

amended as follows: <u>Underlines</u> indicate insertions and <del>strikethrough</del> indicate deletions.

**Listing of claims:** 

1. (Currently cancelled)

2. (Currently Amended) The microporous polymeric article according to claim 13 4,

wherein the target pore diameter  $d_v$  is from 20 nm to 500  $\mu$ m.

3. (Previously Amended) The microporous polymeric article according to claim 2,

wherein the target pore diameter  $d_v$  is from 1 to 72  $\mu$ m.

4. (Previously Amended) The microporous polymeric article according to claim 3,

wherein the majority of pores have a diameter d comprised in a range between d<sub>v</sub>-40%

and  $d_v+40\%$ .

5. (Currently Amended) The microporous polymeric article according to claim 13 4,

wherein the target pore diameter d<sub>v</sub> is from 1 to 3 µm, and wherein the majority of pores

have a diameter d comprised in a range between  $d_v$ -25% and  $d_v$ +25%.

6. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein the porosity is fully continuous.

7. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein the article has a symmetric morphology.

8. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein the article has an asymmetric morphology.

Basil D. Favis

9. (Withdrawn) The microporous biodegradable polymeric article according to claim

8, wherein the article has a closed-cell skin.

10. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein at least 95% of said article is made of a biodegradable medical polymer

selected from the group consisting of poly(lactic acid), poly(glycolic acid), poly(lactic-co-

glycolic), polyorthoesters, polycaprolactones, polyanhydrides and their copolymers.

11. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein at least 99% of said article is made of a biodegradable medical polymer

selected from the group consisting of poly(lactic acid), poly(glycolic acid), poly(lactic-co-

glycolic), polyorthoesters, polycaprolactones, polyanhydrides and their copolymers.

12. (Withdrawn) The microporous biodegradable polymeric article according to claim

1, wherein said article is essentially made of a biocompatible, implantable polymer.

13. (Currently Amended) A microporous polymeric article having a target pore

diameter d<sub>v</sub>, comprising an essentially continuous porosity with a controlled void volume

from 10 to 90%, wherein pore diameters show a unimodal distribution set at a

predefined unimodal peak location corresponding to said target pore diameter d<sub>v</sub>, and

wherein a majority of pores have a diameter d of at least d<sub>v</sub>-50% and at most d<sub>v</sub>+50%,

prepared according to a method comprising the steps of:

a) determining a target pore diameter d<sub>v</sub>;

b) selecting at least one polymer A and at least one polymer B at least

partially immiscible with A, according to the target pore diameter d<sub>v</sub> determined in

step a);

c) melt blending the selected polymers from step a) b), thereby preparing a

polymer blend, wherein said polymers A and B have an essentially continuous

morphology;

d) cooling said polymer blend to room temperature, thereby retaining its

Basil D. Favis

morphology; and

e) extracting said polymer B, at least partially, from the polymer blend by

dissolving said polymer B in a solvent that is a non-solvent of polymer A.

14. (Withdrawn) A method of preparation of a microporous biodegradable polymeric

article, comprising the steps:

a) selecting at least one biodegradable polymer A, one polymer B,

biodegradable or not, at least partially immiscible with A, and a polymeric

compatibilizer C for A and B;

b) melt blending the selected polymers from step a) and the compatibilizer C,

thereby preparing a compatibilized polymer blend, wherein said polymers A and

B have an essentially continuous morphology;

c) cooling said polymer blend to room temperature, thereby retaining its

morphology; and

d) extracting said polymer B and said compatibilizer C, at least partially, from

the polymer blend by dissolving them in a solvent that is a non-solvent of polymer

Α,

wherein said polymeric article has an essentially continuous porosity with a void volume

from 10 to 90%, wherein pore diameters show a unimodal distribution set to a

predefined unimodal peak location corresponding to a chosen pore diameter, and

wherein a majority of pore has a diameter within ± 50% of the chosen pore diameter.

15. (Withdrawn) The method according to claim 14, wherein said polymer A is a

biodegradable medical polymer.

16. (Withdrawn) The method according to claim 15, wherein said polymer A is an

aliphatic polyester.

Application No. 10/552,357 Docket number: 758/12810.114

Supplemental Amendment filed December 6, 2010

Basil D. Favis

17. (Withdrawn) The method according to claim 15, wherein said polymer A is selected from the group consisting of poly(lactic acid), poly(glycolic acid), poly(lactic-co-

glycolic), poly(hydroxyalkanoates), polyorthoesters, polycaprolactones, polydioxanone,

polyanhydrides and their copolymers.

18. (Withdrawn) The method according to claim 14, wherein said polymer B is a non-

biodegradable polymer.

19. (Withdrawn) The method according to claim 14, wherein said polymer B is a

biodegradable medical polymer.

20. (Withdrawn) The method according to claim 19, wherein said polymer B is

selected from a group consisting of poly(lactic acid), poly(glycolic acid), poly(lactic-co-

glycolic), poly(hydroxyalkanoates), polyorthoesters, polycaprolactones, polyanhydrides

and their copolymers.

21. (Withdrawn) The method according to claim 14, wherein said compatibilizer C is

a polymeric compatibilizer.

22. (Withdrawn) The method according to claim 21, wherein said compatibilizer C is

a copolymer of A and B.

23. (Withdrawn) The method according to claim 14, wherein said polymers A and B

are fully immiscible.

24. (Withdrawn) The method according to claim 14, wherein said polymer blend is

co-continuous at more than 90%.

25. (Withdrawn) The method according to claim 14, wherein said polymer blend may

contain one or more additives.

26. (Withdrawn) The method according to claim 14, wherein said polymer blend is

submitted to a further step of controlled annealing between steps b) and c), thereby

increasing the pore size of the porous article.

Basil D. Favis

27. (Withdrawn) The method according to claim 14, wherein said polymer blend is

submitted to controlled cooling rates in step c).

28. (Withdrawn) The method according to claim 14, wherein said polymer blend is

further shaped into a geometrical form between steps b) and c).

29. (Withdrawn) The method according to claim 28, wherein said polymer blend is

further shaped in a mold or die, between steps b) and c).

30. (Withdrawn) The method according to claim 28, wherein said polymer blend is

shaped by injection molding, between steps b) and c).

31. (Withdrawn) The method according to claim 28, wherein said polymer blend is

formed by extrusion, between steps b) and c).

32. (Withdrawn) The method according to claim 28, wherein said polymer blend is

formed by melt spinning between steps b) and c).

33. (Withdrawn) The method according to claim 14, wherein said polymer blend is

submitted to a mechanical stress that orients the porosity in at least one specific

direction, between steps b) and c).

34. (Withdrawn) The method according to claim 14, wherein said polymer blend is

submitted to a mechanical stress that orients the porosity in at least one specific

direction, during step c).

35. (Withdrawn) The method according to claim 14, wherein said polymeric article is

further submitted to a controlled immersion in a solvent for its polymer A after step d),

thereby creating a closed-cell skin.

36. (Withdrawn) The method according to claim 14, wherein said polymer blend is

further submitted to a controlled immersion in a common solvent for A and B between

steps c) and d), thereby creating an asymmetric open-cell morphology in the porous

article.

Basil D. Favis

37. (Currently amended) A method of tissue engineering utilizing a microporous

article according to any one of claims  $\pm 2$  to 5 and 13.

38. (Withdrawn) The use of a microporous biodegradable article obtained by the

method according to any of claims 14-36 in tissue engineering.

39. (Currently amended) A method of controlled release utilizing a microporous

article according to any one of claims 4 - 2 to 5 and 13 as a substrate.

40. (Withdrawn) The use of a microporous biodegradable article obtained by the

method according to any of claims 14-36 as a substrate for controlled release

applications.

41. (Currently amended) A method of forming an implantable medical device utilizing

a microporous article according to any one of claims 4 2 to 5 and 13.

42. (Withdrawn) The use of a microporous biodegradable article obtained by the

method according to any of claims 14-36 as an implantable medical device.

43. (Currently amended) The microporous polymeric article according to any one of

claims 4 2 to 5, said article being biodegradable.

44. (Previously amended) The microporous polymeric article according to claim 13.

wherein step b) further comprises selecting a polymeric compatibilizer C for A and B;

step c) comprises melt blending the selected polymers from step a) and the

compatibilizer C, thereby preparing a compatibilized polymer blend; and step e)

comprises extracting said polymer B and said compatibilizer C, at least partially, from

the polymer blend by dissolving them in a solvent that is a non-solvent of polymer A.